

ID Material: 45
Rble: R. Antich
Revision: 9
Date: 17/03/2017

NR

NR is friction material suitable for medium duty, wet and dry industrial applications. The material consists phenol resins. NR is fully cured and suitable for bonding and riveting. Its success may be attributed to its hardness which gives it good wear and tensile strength while still achieving average and stable friction levels. NR is a material special for hydraulic applications because **this material doesn't contain metallic particles.**

Material data

Friction properties (according graphics)

Static Friction Coefficient (15bar, from box):	0.48±0.05	μ
Static Friction Coefficient (15bar, 100°C):	0.53±0.05	μ
Dynamic Friction Coefficient (10bar, 10m/s):	0.45±0.05	μ
Wear Rate (10bar, 15m/s):	120±10	mm ³ /Kwh
T ^º Fading (10bar, 10m/s):	>350	°C

Physical properties

Hardness (DIN53505):	85±5	Shore-D
Specific Gravity (ASTM D792-91):	1.83±0.05	gr/cm ³
Shear resistance (ISO 6312:2001):	22±2	N/mm ²

Mechanical properties

Tensile Strength (ASTM D638-10):	13±5	N/mm ²
Compressive Strength (UNE 53205):	150±5	N/mm ²
Poisson Coefficient:	0.27±0.03	
Young Modulus (ASTMD 638-10):	3896±100	N/mm ²

Recommended Working Values

T ^º Max. Continuous Operation:	250	°C
T ^º Max. Intermittent Operation:	350	°C

Material type : Rigid material

Appearance / Formats



Applications

Callipers for industrial applications - Cones segments for machinery - Friction pads for hydroelectric applications - Friction washers - Gear discs for industrial devices - Rings segments for machinery -

Price Level : € € €

Reach (EC)1907/2006 - RoHS 2011/65/EU : Compliance

Others

Recommended Mating Surface:	Perlitic cast iron, hardness HB150-200
Recommended Adhesives:	Thermosetting adhesive
Oil Resistant:	Yes

