




## TECHNICAL DATA

DYNAPACK TYPE	DESCRIPTION	TEMP. °C	PH range						
				P.bar	V.m/sec.	P.bar	V.m/sec.	P.bar	V.m/sec.
4180	Pure Graphite yarn - 99% Carbon content - Impregnated with Graphite and corrosion inhibitor.	-100 + 700	0 - 14	40	1	20	3	40	30
3134	Graphite yarn impregnated with Graphite powder and corrosion inhibitor.	-100 + 700	0 - 14	40	1,5	20	2	40	25
3138	Pure Graphite yarn reinforced with Inconel wire and impregnated with Graphite and MOS2.	-100 + 700	0 - 14	200	1				
3136	Pure Carbon yarn impregnated with Graphite, MOS2 and lubricant.	-60 + 500	2 - 12			100	1,5	35	25
4135	CARBOPAN yarn impregnated with Graphite, lubricant and corrosion inhibitor.	-50 + 500	2 - 12	150	1	100	2	45	25
4138	CARBOPAN yarn reinforced with Inconel wire, impregnated with Graphite and corrosion inhibitor.	-50 + 500	1 - 14	200	1				
3180	CARBOPAN yarn impregnated with a special PTFE, Graphite and lubricant compound.	-60 + 280	1 - 13	200	2	100	1,5	50	25
4116	Glass fiber yarn impregnated with PTFE dispersion and lubricant.	-50 + 280	2 - 12	60	1,5	40	2	20	15
4118	Glass fiber yarn impregnated with Graphite and lubricant.	-50 + 500	2 - 12	200	2				
4119	Glass fiber yarn reinforced with Inconel wire, impregnated with Graphite and lubricant.	-50 + 500	2 - 12	300	1				